

TECHNICAL DATASHEET

38.2Mpa

20N

△<2

Pass

0

0-0.2%

α 16.4° R10



zSNAP.DECK WPC

Flexural properties

Scratch resistance

RoHS Requirement

Water absorption after 24 hours in wat

Weathering test after 2000 hours

Slip resistance

Formaldehyde

GENERAL DATA	
CLASSIFICATION	zSNAP.DECK
Dimensions	145 x 22 x 2700 mm
Total Thickness	±1MM
Country of origin	China
Warranty	10 years' warranty against fungal and mold
	Lifetime Workmanship Warranty
TECHNICAL DATA Test condition	Temp.25°C ± -2°C, Humi 50% ± -5%
Density	1.35g/cm3
Hardness	78
Loading capacity	4500N/459KGS (with 30cm span)
Impact resistance	22.8J/M
Coefficient of thermal expansion	1.14 x 10-5 m/m. °C
Tensile properties	22.5Mpa

